

## DAPCO™ 1-100

Dapco™ 1-100 primer is a solution of polymeric materials that cures at room temperature, 75°F (24°C).

Dapco™ 1-100 is used to improve the bond strength between most silicone RTVs and different substrates. When properly applied and cured, the bond strength often exceeds the cohesive strength of the RTV.

### Features and Benefits

- Visible color change to indicate full cure
- Improved bond strength of most RTV silicone systems up to 400°F (204°C)

## CHARACTERISTICS

**Table 1 | Physical Properties**

Property	
Consistency	Liquid
Viscosity at 75°F (24°C)	10 cps (0.01 Pa·s)
Solids (weight)	12%
Density	7.0 lb/gal (0.84 kg/L)
Shelf Life	6 months at 75°F (24°C) from date of shipment

**Table 2 | Product Availability**

Property	
Color	Green <sup>1</sup>
Kit Size	2.0 oz 4.0 oz 8.0 oz Pint

<sup>1</sup> Color dries to dull pink, once cured.

## PROCESSING

### HANDLING

#### Mixing

Dapco™ 1-100 primer is supplied and ready to use. No mixing of the product is required.

#### Working Life

Dapco™ 1-100 primer hydrolyzes (cures) when exposed to the moisture in the air, therefore, it is recommended that the necessary amount of Dapco™ 1-100 is poured into aluminum or glass dish and the bottle resealed.

Note: Dapco™ 1-100 primer contains a flammable solvent. Keep away from open flame and excessive heat and use with adequate ventilation.

## APPLICATION

### Applying

The substrate must be free from contamination, i.e. dirt, oil, grease, etc. Clean the surface by wiping with a suitable solvent/cleaning agent and dry thoroughly. Apply Dapco™ 1-100 primer in a thin, uniform coating.

### Curing

Allow Dapco™ 1-100 to dry for one hour or until a dull pink color is visible. Then apply RTV to primed surface within 90 minutes after the primer has cured. When circumstances prevent immediate application of the RTV, the surface must be cleaned thoroughly to remove the primer before repeating the process. Follow the RTV's individual cure recommendations.

## HEALTH & SAFETY

Please refer to the product SDS for safe handling, personal protective equipment recommendations and disposal considerations.

DISCLAIMER: The data and information provided in this document have been obtained from carefully controlled samples and are considered to be representative of the product described. Solvay does not express or imply any guarantee or warranty of any kind including, but not limited to, the accuracy, the completeness or the relevance of the data and information set out herein. Because the properties of this product can be significantly affected by the fabrication and testing techniques employed, and since Solvay does not control the conditions under which its products are tested and used, Solvay cannot guarantee the properties provided will be obtained with other processes and equipment. No guarantee or warranty is provided if the product is adapted for a specific use or purpose. Solvay declines any liability with respect to the use made by any third party of the data and information contained herein. Solvay has the right to change any data or information when deemed appropriate. All trademarks are the property of their respective owners. ©2016, Solvay. All rights reserved.

---

### Solvay

Composite Materials HQ  
4500 McGinnis Ferry Rd  
Alpharetta, GA 30005-14 USA

TDS DAPCO™ 1-100\_2018\_01\_10

