



NSL1440RC Class A

Aircraft Rapid Cure Integral Fuel Tank Sealant

Replacement For: PR-1440 Class A
 Conforms To: AMS-S-8802 & BMS5-26U by
 FAA-PMA Approval³

Product Description:

NSL1440RC Class A is a fuel resistant sealant for use on integral fuel tanks and pressurized cabins as well as other areas subject to contact with aircraft fuels, lubricants, oils, water and/or weathering.

NSL1440RC Class A is a two-part polysulfide base compound which cures at room temperature to a flexible, resilient rubber.

When mixed, NSL1440RC Class A is a self leveling liquid. For mixed application life details see cure profile below.

Product Features:

- Excellent adhesion to aluminum, magnesium, titanium, steel and numerous other aircraft substrates.
- Designed to withstand the attack of sulfur compounds that are present in jet fuels and aviation gas.
- Service temperature range -65°F(-54°C) to 250°F(121°C) with excursions to 275°F (135 °C).
- Suitable for application by brush to thickness of up to 25 mils.

Heat-Accelerated Curing:

Increased temperature and relative humidity will reduce work life and speed up the cure. Reduced temperature and relative humidity will extend work life and slow the cure.

Cure Profile:

	A-1/2	A-2
Application Life (hrs) ²	1/2	2
Tack Free Time (hrs) ²	<5	<9
Cure Time to 35 Shore A (hrs)	<5	<12

Packaging:

Available in 2½ and 6 oz. cartridges, pint, quart and gallon kits. Also available in premixed and frozen cartridges. Other size packaging available upon request.

Shelf Life:

Sealed containers: 9 months when stored below 80°F. Slight changes in work life, viscosity and curing rate may occur but will not affect end performance of the product.

Typical Properties:

UNCURED

Color: Base	Off-white
Curing Agent	Black
Mixed	Gray
Mixing Ratio: (by weight)	100:12
(by volume)	100:7.8
Non-volatile Content	86%
Viscosity, poise	
Base	250 ¹
Curing Compound	1,000 ¹
Specific Gravity	1.52
Consistency	Self Leveling
CURED – ROOM TEMPERATURE	
Cured – 7 days @ R.T. ²	
Tensile Strength, PSI	250
Elongation, %	250
Durometer, Shore A	50
Min. Peel Strength, PPI	30
Flash Point	90°F

Fungus Resistance

Non-nutrient

¹ Brookfield RVF Spindle #6

² Conditions 77°F and 50% R.H.

³ Material and data depicted on this TDS is provided to Dedicated Packaging, LLC by the approved manufacture supplier(s) for this material. Qualification and inclusion on the QPL(s) is by the supplier(s) per their material identification and conforms as required by the governing specification.

.....
 Dedicated Packaging, LLC FAA PMA
 4 Plum Ct. - Sleepy Hollow, Illinois 60118
 Dedicated Packaging, LLC
 an NSL Aerospace Company

(800) 527.0011
 www.nslaerospace.com